

Ni sulphide ore, CRM, Matrix: mineralised ultramafic, Mineralisation Style: komatiite-hosted nickel sulphide

Art. ID OREAS-74a-10G
Unit 10 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Nickel (Ni)	[7440-02-0]	3,14	%	4-Acid Digestion	
	Platinum (Pt)	[7440-06-4]	223	ppb	Pb Fire Assay	
	Palladium (Pd)	[7440-05-3]	172	ppb	Pb Fire Assay	
	Magnesium oxide (MgO)	[1309-48-4]	27,9	%	Borate and Peroxide Fusion	
	Magnesium oxide (MgO)	[1309-48-4]	28,1	%	4-Acid Digestion	
	Nickel (Ni)	[7440-02-0]	3,24	%	Borate and Peroxide Fusion	
	Al ₂ O ₃		2,2	%	4-Acid Digestion	
	Silicon dioxide (SiO ₂)	[7631-86-9]	32,4	%	Borate and Peroxide Fusion	
	Sulfur (S)	[7704-34-9]	7,25	%	Borate and Peroxide Fusion	
	Sulfur (S)	[7704-34-9]	7,48	%	Infrared Combustion	
	Iron (Fe)	[7439-89-6]	13,8	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	13,7	%	Borate and Peroxide Fusion	
	Gold (Au)	[7440-57-5]	21	ppb	Pb Fire Assay	

				say
Al ₂ O ₃		2,21	%	Borate and Peroxide Fusion
Arsenic (As)	[7440-38-2]	0,00496	%	4-Acid Dig estion
Arsenic (As)	[7440-38-2]	0,00496	%	Borate and Peroxide Fusion
Chromium (Cr)	[7440-47-3]	0,1303	%	4-Acid Dig estion
Chromium (Cr)	[7440-47-3]	0,178	%	Borate and Peroxide Fusion
Cobalt (Co)	[7440-48-4]	0,0554	%	4-Acid Dig estion
Cobalt (Co)	[7440-48-4]	0,0581	%	Borate and Peroxide Fusion
Copper (Cu)	[7440-50-8]	0,1178	%	4-Acid Dig estion
Copper (Cu)	[7440-50-8]	0,124	%	Borate and Peroxide Fusion
Sulfur (S)	[7704-34-9]	7,73	%	4-Acid Dig estion