

Sn ore, Matrix: smectite clay, Mineralisation Style: skarn

Art. ID OREAS-140-500G
Unit 500 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Tin (Sn)	[7440-31-5]	0,1755	%	Borate and Peroxide Fusion	
	Bismuth (Bi)	[7440-69-9]	0,0318	%	4-Acid Dig estion	
	Copper (Cu)	[7440-50-8]	0,1529	%	4-Acid Dig estion	
	Arsenic (As)	[7440-38-2]	0,0149	%	4-Acid Dig estion	
	Tin (Sn)	[7440-31-5]	0,1777	%	Pressed Po wder Pelle t XRF	
	Silver (Ag)	[7440-22-4]	0,000103	%	4-Acid Dig estion	
	Molybdenum (Mo)	[7439-98-7]	0,000168	%	4-Acid Dig estion	
	Lead (Pb)	[7439-92-1]	0,00267	%	4-Acid Dig estion	
	Indium (In)	[7440-74-6]	0,00107	%	4-Acid Dig estion	
	Zinc (Zn)	[7440-66-6]	0,1706	%	4-Acid Dig estion	