

Sn ore, Matrix: smectite clay, Mineralisation Style: skarn

Art. ID OREAS-140-500G
Unit 500 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|-------------------|-------------|---------------------|------|-----------------------------------|--------|
| | Tin (Sn) | [7440-31-5] | 0,1755 | % | Borate and Peroxide Fusion | |
| | Bismuth (Bi) | [7440-69-9] | 0,0318 | % | 4-Acid Dig estion | |
| | Copper (Cu) | [7440-50-8] | 0,1529 | % | 4-Acid Dig estion | |
| | Arsenic (As) | [7440-38-2] | 0,0149 | % | 4-Acid Dig estion | |
| | Tin (Sn) | [7440-31-5] | 0,1777 | % | Pressed Po wder Pelle t XRF | |
| | Silver (Ag) | [7440-22-4] | 0,000103 | % | 4-Acid Dig estion | |
| | Molybdenum (Mo) | [7439-98-7] | 0,000168 | % | 4-Acid Dig estion | |
| | Lead (Pb) | [7439-92-1] | 0,00267 | % | 4-Acid Dig estion | |
| | Indium (In) | [7440-74-6] | 0,00107 | % | 4-Acid Dig estion | |
| | Zinc (Zn) | [7440-66-6] | 0,1706 | % | 4-Acid Dig estion | |