

**Sn ore, Matrix: smectite clay, Mineralisation Style: skarn**

Art. ID                      OREAS-141-500G  
Unit                         500 g  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Tin (Sn)	[7440-31-5]	0,6061	%	Borate and Peroxide Fusion	
	Bismuth (Bi)	[7440-69-9]	0,0324	%	4-Acid Dig estion	
	Copper (Cu)	[7440-50-8]	0,2453	%	4-Acid Dig estion	
	Arsenic (As)	[7440-38-2]	0,0789	%	4-Acid Dig estion	
	Tin (Sn)	[7440-31-5]	0,6312	%	Pressed Po wder Pelle t XRF	
	Silver (Ag)	[7440-22-4]	0,000158	%	4-Acid Dig estion	
	Molybdenum (Mo)	[7439-98-7]	0,000228	%	4-Acid Dig estion	
	Lead (Pb)	[7439-92-1]	0,0059	%	4-Acid Dig estion	
	Indium (In)	[7440-74-6]	0,0034	%	4-Acid Dig estion	
	Zinc (Zn)	[7440-66-6]	0,3637	%	4-Acid Dig estion	