

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-155
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		10,2	%		
	CaO		34,35	%		
	Cr ₂ O ₃		0,68	%		
	Iron (Fe)	[7439-89-6]	13,17	%		
	FeO		0,11	%		
	MgO	[1309-48-4]	4,70	%		
	MnO		3,91	%		
	P ₂ O ₅		4,26	%		
	Sulfur (S)	[7704-34-9]	0,124	%		
	SiO ₂		19,19	%		
	TiO ₂		0,38	%		
	Carbon (C)	[7440-44-0]	0,39	%		