

## **CEN-Standard Sand according to EN 196-1**

Art. ID	NOS-001-36x1350G
Unit	bag (36 x 1350 g)
Deliverydetails	No Dangerous Good /not restricted

### Description

The characteristic of CEN-Standard Sand is its specific grain size distribution. It ranges between 0.08 and 2.00 mm. The grain size distribution is drawn in the picture (cumulated sieve residue in % vs squared mesh size in mm) and listed in the table below. The maximum moisture content is 0.2%. The sand is portioned in bags of 1350 ( $\pm 5$ ) g. According to EN 196-1 mortar prisms for compressive strength testing are produced with a mixture of 450 ( $\pm 2$ ) g cement, 225 ( $\pm 1$ ) g water and one bag of 1350 ( $\pm 5$ ) g CEN-Standard Sand.