

RESIN BONDED GLASS FIBRE BOARD (thermal conductivity)

Art. ID ERM-FC440B
Unit board 50 x 50 cm
Deliverydetails No Dangerous Good /not restricted

Description

Thermal conductivity: As determined by the guarded hot plate method according to ISO 8302:1991 or EN 12667:2001

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
As a function of test temperature T in °C for -10 °C <= T <= 70 °C	Thermal conductivity		31,04 + 0,11 ± 0,1 T/°C	mW/(m·K)		