

RESIN BONDED GLASS FIBRE BOARD (thermal conductivity)

Art. ID ERM-FC440C
Unit board 60 x 60 cm
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
As a function of test t emperature T in °C for -10 °C <= T <= 70 °C	Thermal conductivity		31,04 + 0,11 ± 0,1 T/°C	mW/(m·K)		