

Iron Base, Steel - Silicon, SUS RFED, Disc 40 mm x 40 mm

| | |
|-----------------|-----------------------------------|
| Art. ID | SUS-R-Fe-D |
| Unit | disc |
| Deliverydetails | No Dangerous Good /not restricted |

Description

Please note that the values varies from lot to lot.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|-------------------|--------------|---------------------|------|--------|--------|
| | Aluminium (Al) | [7429-90-5] | 0,11 | % | | |
| | Antimony (Sb) | [7440-36-0] | 0,1 | % | | |
| | Arsenic (As) | [7440-38-2] | 0,007 | % | | |
| | Bismuth (Bi) | [7440-69-9] | <0,01 | % | | |
| | Boron (B) | [7440-42-8] | <0,01 | % | | |
| | Carbon (C) | [7440-44-0] | 0,81 | % | | |
| | Chromium (Cr) | [7440-47-3] | 3,11 | % | | |
| | Cobalt (Co) | [7440-48-4] | 0,28 | % | | |
| | Copper (Cu) | [7440-50-8] | 0,08 | % | | |
| | Lead (Pb) | [7439-92-1] | 0,01 | % | | |
| | Manganese (Mn) | [7439-96-5] | 0,32 | % | | |
| | Molybdenum (Mo) | [7439-98-7] | 1,25 | % | | |
| | Nickel (Ni) | [7440-02-0] | 0,12 | % | | |
| | Niobium (Nb) | [7440-03-1] | 0,42 | % | | |
| | Nitrogen (N) | [7727-37-9] | 0,02 | % | | |
| | Phosphorus (P) | [7723-14-0] | 0,03 | % | | |
| | Silicon (Si) | [7440-21-3] | 1,3 | % | | |
| | Sulfur (S) | [7704-34-9] | 0,01 | % | | |
| | Tantalum (Ta) | [7440-25-7] | 0,06 | % | | |
| | Tellurium (Te) | [13494-80-9] | 0,01 | % | | |
| | Tin (Sn) | [7440-31-5] | 0,01 | % | | |
| | Titanium (Ti) | [7440-32-6] | 0,15 | % | | |
| | Tungsten (W) | [7440-33-7] | 0,05 | % | | |
| | Vanadium (V) | [7440-62-2] | 0,09 | % | | |