

Duplex stainless steel, similar to EN 1.4410 - chips

Art. ID	ECRM-S 298-2
Unit	100 g
Deliverydetails	No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	0,0148 ± 0,0008	%		
	Arsenic (As)	[7440-38-2]	0,0028 ± 0,0002	%		
	Boron (B)	[7440-42-8]	0,0024 ± 0,0002	%		
	Carbon (C)	[7440-44-0]	0,014 ± 0,0006	%		
	Cobalt (Co)	[7440-48-4]	0,0482 ± 0,0008	%		
	Chromium (Cr)	[7440-47-3]	24,91 ± 0,06	%		
	Copper (Cu)	[7440-50-8]	0,105 ± 0,002	%		
	Manganese (Mn)	[7439-96-5]	0,786 ± 0,007	%		
	Molybdenum (Mo)	[7439-98-7]	3,781 ± 0,029	%		
	Nitrogen (N)	[7727-37-9]	0,277 ± 0,006	%		
	Niobium (Nb)	[7440-03-1]	0,0011 ± 0,0001	%		
	Nickel (Ni)	[7440-02-0]	6,877 ± 0,021	%		
	Phosphorus (P)	[7723-14-0]	0,021 ± 0,0006	%		
	Sulfur (S)	[7704-34-9]	0,0006 ± 0,0002	%		
	Antimony (Sb)	[7440-36-0]	0,0006 ± 0,0001	%		
	Silicon (Si)	[7440-21-3]	0,331 ± 0,007	%		
	Tin (Sn)	[7440-31-5]	0,0029 ± 0,0001	%		
	Titanium (Ti)	[7440-32-6]	0,0023 ± 0,0001	%		
	Vanadium (V)	[7440-62-2]	0,0704 ± 0,001	%		
	Tungsten (W)	[7440-33-7]	0,0094 ± 0,0005	%		
	Alloy / Werkstoff		1.4410			