

*****sold out*** Bauxite, CRM, Pulp Bauxite, Darling Range, Western Australia, Powder 10 g**

Art. ID GEO-GBAP-14
Unit 10 g (powder)

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		14,32	%		
	Al ₂ O ₃		35,07	%		
	Arsenic (As)	[7440-38-2]	~0,003	%		
	BaO		~0,006	%		
	CaO		0,03	%		
	Cr ₂ O ₃		0,122	%		
	Fe ₂ O ₃		40,67	%		
	K ₂ O		0,073	%		
	MgO	[1309-48-4]	0,042	%		
	MnO		0,017	%		
	Na ₂ O		0,024	%		
	P ₂ O ₅		0,042	%		
	SO ₃		0,145	%		
	SiO ₂		6,74	%		
	TiO ₂		2,502	%		
	V ₂ O ₅		0,177	%		
	ZrO ₂		0,062	%		