

Refractory, CRM, set of 12 x 20 g (1 x 20 g each of JRRM-321, JRRM-322, JRRM-323, JRRM-324, JRRM-325, JRRM-326, JRRM-327, JRRM-328, JRRM-329, JRRM-330, JRRM-331 and JRRM-332), Powder

Art. ID JRRM-321-332
Unit 12 x 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
JRRM-321: Refractory, C RM, Powder	Al ₂ O ₃		38,9	%		
JRRM-321: Refractory, C RM, Powder	CaO		0,92	%		
JRRM-321: Refractory, C RM, Powder	Cr ₂ O ₃		0,99	%		
JRRM-321: Refractory, C RM, Powder	Fe ₂ O ₃		3,97	%		
JRRM-321: Refractory, C RM, Powder	K ₂ O		2,28	%		
JRRM-321: Refractory, C RM, Powder	MgO	[1309-48-4]	3,18	%		
JRRM-321: Refractory, C RM, Powder	MnO		0,06	%		
JRRM-321: Refractory, C RM, Powder	Na ₂ O		0,46	%		
JRRM-321: Refractory, C RM, Powder	P ₂ O ₅		3,36	%		
JRRM-321: Refractory, C RM, Powder	SiO ₂		44,6	%		
JRRM-321: Refractory, C RM, Powder	TiO ₂		0,94	%		
JRRM-321: Refractory, C RM, Powder	ZrO ₂		0,02	%		
JRRM-322: Refractory, C RM, Powder	Al ₂ O ₃		49,7	%		
JRRM-322: Refractory, C RM, Powder	CaO		1,1	%		
JRRM-322: Refractory, C RM, Powder	Cr ₂ O ₃		0,05	%		

JRRM-322: Refractory, C	Fe2O3		4,51	%
RM, Powder				
JRRM-322: Refractory, C	K2O		0,71	%
RM, Powder				
JRRM-322: Refractory, C	MgO	[1309-48-4]	0,6	%
RM, Powder				
JRRM-322: Refractory, C	MnO		0,29	%
RM, Powder				
JRRM-322: Refractory, C	Na2O		1,1	%
RM, Powder				
JRRM-322: Refractory, C	P2O5		0,64	%
RM, Powder				
JRRM-322: Refractory, C	SiO2		39,8	%
RM, Powder				
JRRM-322: Refractory, C	TiO2		0,57	%
RM, Powder				
JRRM-322: Refractory, C	ZrO2		0,51	%
RM, Powder				
JRRM-323: Refractory, C	Al2O3		55,8	%
RM, Powder				
JRRM-323: Refractory, C	CaO		2,07	%
RM, Powder				
JRRM-323: Refractory, C	Cr2O3		0,2	%
RM, Powder				
JRRM-323: Refractory, C	Fe2O3		1,7	%
RM, Powder				
JRRM-323: Refractory, C	K2O		0,19	%
RM, Powder				
JRRM-323: Refractory, C	MgO	[1309-48-4]	2,71	%
RM, Powder				
JRRM-323: Refractory, C	MnO		0,23	%
RM, Powder				
JRRM-323: Refractory, C	Na2O		1,45	%
RM, Powder				
JRRM-323: Refractory, C	P2O5		2,63	%
RM, Powder				
JRRM-323: Refractory, C	SiO2		31,8	%
RM, Powder				

JRRM-323: Refractory, C	TiO ₂		0,2	%
RM, Powder				
JRRM-323: Refractory, C	ZrO ₂		0,65	%
RM, Powder				
JRRM-324: Refractory, C	Al ₂ O ₃		62,7	%
RM, Powder				
JRRM-324: Refractory, C	CaO		0,31	%
RM, Powder				
JRRM-324: Refractory, C	Cr ₂ O ₃		0,3	%
RM, Powder				
JRRM-324: Refractory, C	Fe ₂ O ₃		3,3	%
RM, Powder				
JRRM-324: Refractory, C	K ₂ O		0,39	%
RM, Powder				
JRRM-324: Refractory, C	MgO	[1309-48-4]	0,97	%
RM, Powder				
JRRM-324: Refractory, C	MnO		0,09	%
RM, Powder				
JRRM-324: Refractory, C	Na ₂ O		0,12	%
RM, Powder				
JRRM-324: Refractory, C	P ₂ O ₅		1,55	%
RM, Powder				
JRRM-324: Refractory, C	SiO ₂		24,9	%
RM, Powder				
JRRM-324: Refractory, C	TiO ₂		4,98	%
RM, Powder				
JRRM-325: Refractory, C	Al ₂ O ₃		68,9	%
RM, Powder				
JRRM-325: Refractory, C	CaO		0,7	%
RM, Powder				
JRRM-325: Refractory, C	Cr ₂ O ₃		0,03	%
RM, Powder				
JRRM-325: Refractory, C	Fe ₂ O ₃		2,47	%
RM, Powder				
JRRM-325: Refractory, C	K ₂ O		3,08	%
RM, Powder				
JRRM-325: Refractory, C	MgO	[1309-48-4]	0,26	%
RM, Powder				

JRRM-325: Refractory, C	MnO		0,01	%
RM, Powder				
JRRM-325: Refractory, C	Na2O		1,69	%
RM, Powder				
JRRM-325: Refractory, C	P2O5		0,14	%
RM, Powder				
JRRM-325: Refractory, C	SiO2		19,9	%
RM, Powder				
JRRM-325: Refractory, C	TiO2		2,24	%
RM, Powder				
JRRM-325: Refractory, C	ZrO2		0,04	%
RM, Powder				
JRRM-326: Refractory, C	Al2O3		73,8	%
RM, Powder				
JRRM-326: Refractory, C	CaO		0,49	%
RM, Powder				
JRRM-326: Refractory, C	Cr2O3		0,49	%
RM, Powder				
JRRM-326: Refractory, C	Fe2O3		1,88	%
RM, Powder				
JRRM-326: Refractory, C	K2O		1,69	%
RM, Powder				
JRRM-326: Refractory, C	MgO	[1309-48-4]	0,39	%
RM, Powder				
JRRM-326: Refractory, C	MnO		0,02	%
RM, Powder				
JRRM-326: Refractory, C	Na2O		1,83	%
RM, Powder				
JRRM-326: Refractory, C	P2O5		0,31	%
RM, Powder				
JRRM-326: Refractory, C	SiO2		15,9	%
RM, Powder				
JRRM-326: Refractory, C	TiO2		2,62	%
RM, Powder				
JRRM-326: Refractory, C	ZrO2		0,3	%
RM, Powder				
JRRM-327: Refractory, C	Al2O3		76,3	%
RM, Powder				

JRRM-327: Refractory, C	CaO		0,21	%
RM, Powder				
JRRM-327: Refractory, C	Cr2O3		0,68	%
RM, Powder				
JRRM-327: Refractory, C	Fe2O3		3,06	%
RM, Powder				
JRRM-327: Refractory, C	K2O		2,89	%
RM, Powder				
JRRM-327: Refractory, C	MgO	[1309-48-4]	1,48	%
RM, Powder				
JRRM-327: Refractory, C	MnO		0,14	%
RM, Powder				
JRRM-327: Refractory, C	Na2O		2,16	%
RM, Powder				
JRRM-327: Refractory, C	P2O5		0,55	%
RM, Powder				
JRRM-327: Refractory, C	SiO2		9,97	%
RM, Powder				
JRRM-327: Refractory, C	TiO2		1,45	%
RM, Powder				
JRRM-327: Refractory, C	ZrO2		0,99	%
RM, Powder				
JRRM-328: Refractory, C	Al2O3		85,8	%
RM, Powder				
JRRM-328: Refractory, C	CaO		0,1	%
RM, Powder				
JRRM-328: Refractory, C	Cr2O3		0,1	%
RM, Powder				
JRRM-328: Refractory, C	Fe2O3		0,2	%
RM, Powder				
JRRM-328: Refractory, C	K2O		0,1	%
RM, Powder				
JRRM-328: Refractory, C	MgO	[1309-48-4]	0,05	%
RM, Powder				
JRRM-328: Refractory, C	MnO		0,18	%
RM, Powder				
JRRM-328: Refractory, C	Na2O		0,6	%
RM, Powder				

JRRM-328: Refractory, C	P2O5		1,97	%
RM, Powder				
JRRM-328: Refractory, C	SiO2		7,05	%
RM, Powder				
JRRM-328: Refractory, C	TiO2		3,36	%
RM, Powder				
JRRM-329: Refractory, C	Al2O3		85,5	%
RM, Powder				
JRRM-329: Refractory, C	CaO		1,49	%
RM, Powder				
JRRM-329: Refractory, C	Cr2O3		0,37	%
RM, Powder				
JRRM-329: Refractory, C	Fe2O3		1,01	%
RM, Powder				
JRRM-329: Refractory, C	K2O		1,34	%
RM, Powder				
JRRM-329: Refractory, C	MgO	[1309-48-4]	0,21	%
RM, Powder				
JRRM-329: Refractory, C	MnO		0,03	%
RM, Powder				
JRRM-329: Refractory, C	Na2O		0,86	%
RM, Powder				
JRRM-329: Refractory, C	P2O5		0,08	%
RM, Powder				
JRRM-329: Refractory, C	SiO2		2,01	%
RM, Powder				
JRRM-329: Refractory, C	TiO2		3,78	%
RM, Powder				
JRRM-329: Refractory, C	ZrO2		0,15	%
RM, Powder				
JRRM-330: Refractory, C	Al2O3		92,4	%
RM, Powder				
JRRM-330: Refractory, C	CaO		0,04	%
RM, Powder				
JRRM-330: Refractory, C	Cr2O3		0,01	%
RM, Powder				
JRRM-330: Refractory, C	Fe2O3		0,03	%
RM, Powder				

JRRM-330: Refractory, C	K2O		0,99	%
RM, Powder				
JRRM-330: Refractory, C	MgO	[1309-48-4]	1,95	%
RM, Powder				
JRRM-330: Refractory, C	Na2O		0,23	%
RM, Powder				
JRRM-330: Refractory, C	P2O5		0,98	%
RM, Powder				
JRRM-330: Refractory, C	SiO2		0,97	%
RM, Powder				
JRRM-330: Refractory, C	TiO2		1,92	%
RM, Powder				
JRRM-331: Refractory, C	Al2O3		99	%
RM, Powder				
JRRM-331: Refractory, C	CaO		0,03	%
RM, Powder				
JRRM-331: Refractory, C	Fe2O3		0,11	%
RM, Powder				
JRRM-331: Refractory, C	K2O		0,12	%
RM, Powder				
JRRM-331: Refractory, C	MgO	[1309-48-4]	0,02	%
RM, Powder				
JRRM-331: Refractory, C	Na2O		0,28	%
RM, Powder				
JRRM-331: Refractory, C	P2O5		0,08	%
RM, Powder				
JRRM-331: Refractory, C	SiO2		0,23	%
RM, Powder				
JRRM-331: Refractory, C	TiO2		0,01	%
RM, Powder				
JRRM-331: Refractory, C	ZrO2		0,04	%
RM, Powder				
JRRM-332: Refractory, C	Al2O3		99,9	%
RM, Powder				