

Stainless Steel, Austenitic, AISI 303 / S30300, Disc 38 mm x 40 mm

Art. ID IARM-FE303-18-40MM
Unit disc
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Arsenic (As)	[7440-38-2]	0,007	%		
	Boron (B)	[7440-42-8]	~0,0012	%		
	Carbon (C)	[7440-44-0]	0,046	%		
	Cobalt (Co)	[7440-48-4]	0,14	%		
	Chromium (Cr)	[7440-47-3]	17,2	%		
	Copper (Cu)	[7440-50-8]	0,61	%		
	Manganese (Mn)	[7439-96-5]	1,55	%		
	Molybdenum (Mo)	[7439-98-7]	0,42	%		
	Nitrogen (N)	[7727-37-9]	0,069	%		
	Niobium (Nb)	[7440-03-1]	0,015	%		
	Nickel (Ni)	[7440-02-0]	8,12	%		
	Oxygen (O)	[7782-44-7]	~0,006	%		
	Phosphorus (P)	[7723-14-0]	0,033	%		
	Sulfur (S)	[7704-34-9]	0,35	%		
	Silicon (Si)	[7440-21-3]	0,47	%		
	Tin (Sn)	[7440-31-5]	~0,015	%		
	Vanadium (V)	[7440-62-2]	0,072	%		
	Tungsten (W)	[7440-33-7]	0,029	%		
	Arsenic (As)	[7440-38-2]	0,007	%		
	Boron (B)	[7440-42-8]	~0,0012	%		
	Carbon (C)	[7440-44-0]	0,046	%		
	Cobalt (Co)	[7440-48-4]	0,14	%		
	Chromium (Cr)	[7440-47-3]	17,2	%		
	Copper (Cu)	[7440-50-8]	0,61	%		
	Manganese (Mn)	[7439-96-5]	1,55	%		
	Molybdenum (Mo)	[7439-98-7]	0,42	%		
	Nitrogen (N)	[7727-37-9]	0,069	%		
	Niobium (Nb)	[7440-03-1]	0,015	%		
	Nickel (Ni)	[7440-02-0]	8,12	%		
	Oxygen (O)	[7782-44-7]	~0,006	%		
	Phosphorus (P)	[7723-14-0]	0,033	%		

Sulfur (S)	[7704-34-9]	0,35	%
Silicon (Si)	[7440-21-3]	0,47	%
Tin (Sn)	[7440-31-5]	~0,015	%
Vanadium (V)	[7440-62-2]	0,072	%
Tungsten (W)	[7440-33-7]	0,029	%