

Iron base, CRM for Low Alloy 300M - UNS Number K44220, Disc 38 mm x 7 mm XRF CUT

Art. ID BS-300B-7MM
Unit disc
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	0,04	%		
	Arsenic (As)	[7440-38-2]	0,003	%		
	Boron (B)	[7440-42-8]	<0,005	%		
	Carbon (C)	[7440-44-0]	0,41	%		
	Calcium (Ca)	[7440-70-2]	<0,005	%		
	Cobalt (Co)	[7440-48-4]	0,012	%		
	Chromium (Cr)	[7440-47-3]	0,79	%		
	Copper (Cu)	[7440-50-8]	0,067	%		
	Iron (Fe)	[7439-89-6]	94	%		
	Hydrogen (H)	[1333-74-0]	<0,005	%		
	Manganese (Mn)	[7439-96-5]	0,71	%		
	Molybdenum (Mo)	[7439-98-7]	0,4	%		
	Nitrogen (N)	[7727-37-9]	<0,05	%		
	Niobium (Nb)	[7440-03-1]	0,003	%		
	Nickel (Ni)	[7440-02-0]	1,86	%		
	Oxygen (O)	[7782-44-7]	<0,005	%		
	Phosphorus (P)	[7723-14-0]	0,005	%		
	Lead (Pb)	[7439-92-1]	<0,005	%		
	Sulfur (S)	[7704-34-9]	0,0007	%		
	Antimony (Sb)	[7440-36-0]	<0,05	%		
	Silicon (Si)	[7440-21-3]	1,65	%		
	Tin (Sn)	[7440-31-5]	0,005	%		
	Tantalum (Ta)	[7440-25-7]	<0,05	%		
	Titanium (Ti)	[7440-32-6]	0,003	%		
	Vanadium (V)	[7440-62-2]	0,078	%		
	Tungsten (W)	[7440-33-7]	0,001	%		
	Zirconium (Zr)	[7440-67-7]	0,001	%		