

Low alloy Steel for solid spectrometry, combustion and wet-way methods, Chips

Art. ID CZ-SPL-304A-Chips
Unit 100 g (chips)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Iron (Fe)	[7439-89-6]	Base			
	Carbon (C)	[7440-44-0]	0,369	%		
	Manganese (Mn)	[7439-96-5]	0,121	%		
	Silicon (Si)	[7440-21-3]	0,854	%		
	Phosphorus (P)	[7723-14-0]	0,0274	%		
	Sulfur (S)	[7704-34-9]	0,062	%		
	Copper (Cu)	[7440-50-8]	0,066	%		
	Chromium (Cr)	[7440-47-3]	0,434	%		
	Nickel (Ni)	[7440-02-0]	5,04	%		
	Aluminium (Al)	[7429-90-5]	0,0327	%		
	Molybdenum (Mo)	[7439-98-7]	0,131	%		
	Tungsten (W)	[7440-33-7]	1,319	%		
	Vanadium (V)	[7440-62-2]	0,17	%		
	Titanium (Ti)	[7440-32-6]	0,175	%		
	Cobalt (Co)	[7440-48-4]	0,034	%		
	Arsenic (As)	[7440-38-2]	0,0194	%		
	Tin (Sn)	[7440-31-5]	0,0302	%		
	Boron (B)	[7440-42-8]	0,0041	%		
	Niobium (Nb)	[7440-03-1]	0,0176	%		
	Antimony (Sb)	[7440-36-0]	0,008	%		
	Lead (Pb)	[7439-92-1]	0,033	%		
	Zirconium (Zr)	[7440-67-7]	0,057	%		
	Nitrogen (N)	[7727-37-9]	0,0081	%		
	Bismuth (Bi)	[7440-69-9]	~0,002	%		
	Cerium (Ce)	[7440-45-1]	~0,004	%		
	Germanium (Ge)	[7440-56-4]	~0,014	%		