

Refractory, CRM, Al-Zr-Si, set of 10 x 20 g (1 x 20 g each of JRRM-701, JRRM-702, JRRM-703, JRRM-704, JRRM-705, JRRM-706, JRRM-707, JRRM-708, JRRM-709 and JRRM-710), Powder

Art. ID JRRM-701-710
Unit 10 x 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	Loss on Ignition (LOI)		~0,09	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	Al ₂ O ₃		10,09	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	CaO		2,07	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	Cr ₂ O ₃		1,01	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	Fe ₂ O ₃		2	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	HfO ₂		0,85	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	K ₂ O		0,02	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	MgO	[1309-48-4]	0,47	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	Na ₂ O		1,84	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	P ₂ O ₅		~0,02	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	SiO ₂		28,44	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	TiO ₂		4,96	%		
JRRM-701: Refractory, C RM, Al-Zr-Si, Powder	ZrO ₂		48,06	%		
JRRM-702: Refractory, C RM, Al-Zr-Si, Powder	Loss on Ignition (LOI)		~0,18	%		
JRRM-702: Refractory, C RM, Al-Zr-Si, Powder	Al ₂ O ₃		38,14	%		

JRRM-702: Refractory, C	CaO		1,55	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	Cr ₂ O ₃		0,11	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	Fe ₂ O ₃		0,37	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	HfO ₂		2,08	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	K ₂ O		0,57	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	MgO	[1309-48-4]	1,97	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	Na ₂ O		2,02	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	P ₂ O ₅		~0,02	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	SiO ₂		9,99	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	TiO ₂		0,21	%
RM, Al-Zr-Si, Powder				
JRRM-702: Refractory, C	ZrO ₂		42,54	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	Loss on Ignition (LOI)		~0,09	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	Al ₂ O ₃		46,34	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	CaO		0,03	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	Fe ₂ O ₃		0,05	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	HfO ₂		0,72	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	MgO	[1309-48-4]	0,01	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	Na ₂ O		0,53	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	P ₂ O ₅		~0,03	%
RM, Al-Zr-Si, Powder				

JRRM-703: Refractory, C	SiO ₂		14,64	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	TiO ₂		0,07	%
RM, Al-Zr-Si, Powder				
JRRM-703: Refractory, C	ZrO ₂		37,35	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	Loss on Ignition (LOI)		~0,07	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	Al ₂ O ₃		19,58	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	CaO		0,15	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	Cr ₂ O ₃		0,51	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	Fe ₂ O ₃		0,55	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	HfO ₂		0,68	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	K ₂ O		1,4	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	MgO	[1309-48-4]	0,51	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	MnO		~0,08	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	Na ₂ O		0,22	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	P ₂ O ₅		~0,13	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	SiO ₂		42,61	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	TiO ₂		1,02	%
RM, Al-Zr-Si, Powder				
JRRM-704: Refractory, C	ZrO ₂		33,46	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	Loss on Ignition (LOI)		~0,16	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	Al ₂ O ₃		64,14	%
RM, Al-Zr-Si, Powder				

JRRM-705: Refractory, C	CaO		0,19	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	Cr ₂ O ₃		2,01	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	Fe ₂ O ₃		0,14	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	HfO ₂		0,48	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	K ₂ O		0,01	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	MgO	[1309-48-4]	0,46	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	Na ₂ O		0,3	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	P ₂ O ₅		~0,01	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	SiO ₂		1,99	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	TiO ₂		2,02	%
RM, Al-Zr-Si, Powder				
JRRM-705: Refractory, C	ZrO ₂		27,96	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	Loss on Ignition (LOI)		~0,72	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	Al ₂ O ₃		25,95	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	CaO		1,58	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	Cr ₂ O ₃		0,01	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	Fe ₂ O ₃		0,13	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	HfO ₂		1,19	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	K ₂ O		0,95	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	MgO	[1309-48-4]	0,15	%
RM, Al-Zr-Si, Powder				

JRRM-706: Refractory, C	Na2O		3,49	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	P2O5		~0,01	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	SiO2		39,33	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	TiO2		3,77	%
RM, Al-Zr-Si, Powder				
JRRM-706: Refractory, C	ZrO2		22,72	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	Loss on Ignition (LOI)		~0,01	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	Al2O3		55,78	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	CaO		1,08	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	Cr2O3		0,18	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	Fe2O3		1,81	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	HfO2		0,36	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	K2O		0,15	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	MgO	[1309-48-4]	0,84	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	Na2O		0,19	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	P2O5		~0,05	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	SiO2		21,17	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	TiO2		0,28	%
RM, Al-Zr-Si, Powder				
JRRM-707: Refractory, C	ZrO2		18,16	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	Loss on Ignition (LOI)		~0,13	%
RM, Al-Zr-Si, Powder				

JRRM-708: Refractory, C	Al ₂ O ₃		79,52	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	CaO		1,17	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	Cr ₂ O ₃		0,29	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	Fe ₂ O ₃		0,8	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	HfO ₂		1,03	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	K ₂ O		0,74	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	MgO	[1309-48-4]	1,64	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	Na ₂ O		0,08	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	SiO ₂		0,54	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	TiO ₂		1,02	%
RM, Al-Zr-Si, Powder				
JRRM-708: Refractory, C	ZrO ₂		12,84	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	Loss on Ignition (LOI)		~0,2	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	Al ₂ O ₃		50,35	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	CaO		0,52	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	Cr ₂ O ₃		2,91	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	Fe ₂ O ₃		0,47	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	HfO ₂		0,18	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	K ₂ O		0,21	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	MgO	[1309-48-4]	1,2	%
RM, Al-Zr-Si, Powder				

JRRM-709: Refractory, C	Na ₂ O		1,03	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	SiO ₂		34,38	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	TiO ₂		0,09	%
RM, Al-Zr-Si, Powder				
JRRM-709: Refractory, C	ZrO ₂		8,32	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	Loss on Ignition (LOI)		~0,09	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	Al ₂ O ₃		82,29	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	CaO		0,22	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	Cr ₂ O ₃		1,02	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	Fe ₂ O ₃		1,15	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	HfO ₂		1,51	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	K ₂ O		0,63	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	MgO	[1309-48-4]	0,04	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	Na ₂ O		1,41	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	P ₂ O ₅		~0,04	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	SiO ₂		5,62	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	TiO ₂		3	%
RM, Al-Zr-Si, Powder				
JRRM-710: Refractory, C	ZrO ₂		2,96	%
RM, Al-Zr-Si, Powder				