

Glass, SUS, Disc 40 mm Ø x 5 mm

| | |
|-----------------|-----------------------------------|
| Art. ID | XRF-BR-7/L |
| Unit | disc |
| Deliverydetails | No Dangerous Good /not restricted |

Description

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 0,91 | % | | |
| | B ₂ O ₃ | | 9,63 | % | | |
| | BaO | | 45,6 | % | | |
| | CaO | | 3,23 | % | | |
| | Fe ₂ O ₃ | | 0,03 | % | | |
| | K ₂ O | | 0,12 | % | | |
| | Na ₂ O | | 0,06 | % | | |
| | PbO | | 0,26 | % | | |
| | Sb ₂ O ₃ | | 0,62 | % | | |
| | SiO ₂ | | 30,6 | % | | |
| | SrO | | 0,27 | % | | |
| | TiO ₂ | | 2,78 | % | | |
| | ZnO | | 5,27 | % | | |