

### **Glass, SUS, Disc 40 mm Ø x 5 mm**

Art. ID	XRF-BR-AX1
Unit	disc
Deliverydetails	No Dangerous Good /not restricted

#### **Description**

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		5,67	%		
	As <sub>2</sub> O <sub>3</sub>		0,6	%		
	B <sub>2</sub> O <sub>3</sub>		5	%		
	Bi <sub>2</sub> O <sub>3</sub>		0,0055	%		
	CaO		2,8	%		
	CuO		2,5	%		
	Fluorine (F)	[7782-41-4]	14	%		
	Fe <sub>2</sub> O <sub>3</sub>		4,29	%		
	K <sub>2</sub> O		6,02	%		
	MgO	[1309-48-4]	0,83	%		
	MoO <sub>3</sub>		0,0058	%		
	P <sub>2</sub> O <sub>5</sub>		1,15	%		
	PbO		1,08	%		
	SO <sub>3</sub>		1,25	%		
	SiO <sub>2</sub>		52,31	%		
	ZnO		2,49	%		