

### **Glass, SUS, Cement, Disc 40 mm Ø x 5 mm**

Art. ID	XRF-BR-BCEM
Unit	disc
Deliverydetails	No Dangerous Good /not restricted

#### **Description**

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		4,88	%		
	B <sub>2</sub> O <sub>3</sub>		2,4	%		
	CaO		35	%		
	Fe <sub>2</sub> O <sub>3</sub>		2,25	%		
	K <sub>2</sub> O		0,99	%		
	MgO	[1309-48-4]	2,37	%		
	Mn <sub>2</sub> O <sub>3</sub>		0,01	%		
	Na <sub>2</sub> O		2,12	%		
	P <sub>2</sub> O <sub>5</sub>		0,01	%		
	SO <sub>3</sub>		0,5	%		
	Sb <sub>2</sub> O <sub>3</sub>		0,31	%		
	SiO <sub>2</sub>		49,15	%		
	TiO <sub>2</sub>		0,01	%		