

Glass, SUS, Disc 40 mm ? x 5 mm

| | |
|-----------------|-----------------------------------|
| Art. ID | XRF-BR-GE2 |
| Unit | disc |
| Deliverydetails | No Dangerous Good /not restricted |

Description

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 0,75 | % | | |
| | BaO | | 0,025 | % | | |
| | CaO | | 0,15 | % | | |
| | CdO | | 0,8 | % | | |
| | Fluorine (F) | [7782-41-4] | 0,4 | % | | |
| | Fe ₂ O ₃ | | 0,1 | % | | |
| | K ₂ O | | 7,5 | % | | |
| | Li ₂ O | | 0,1 | % | | |
| | Na ₂ O | | 9,5 | % | | |
| | PbO | | 0,05 | % | | |
| | SO ₃ | | 0,5 | % | | |
| | Sb ₂ O ₃ | | 0,5 | % | | |
| | Selenium (Se) | [7782-49-2] | 0,15 | % | | |
| | SiO ₂ | | 67,9 | % | | |
| | TiO ₂ | | 0,025 | % | | |
| | ZnO | | 11,5 | % | | |
| | ZrO ₂ | | 0,05 | % | | |