

Glass, SUS, Disc 40 mm Ø x 5 mm

| | |
|-----------------|-----------------------------------|
| Art. ID | XRF-BR-HKM2 |
| Unit | disc |
| Deliverydetails | No Dangerous Good /not restricted |

Description

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 11 | % | | |
| | B ₂ O ₃ | | 5,98 | % | | |
| | CuO | | 0,03 | % | | |
| | Fe ₂ O ₃ | | 3 | % | | |
| | K ₂ O | | 5 | % | | |
| | Mn ₃ O ₄ | | 5 | % | | |
| | MoO ₃ | | 4 | % | | |
| | Na ₂ O | | 10 | % | | |
| | Nb ₂ O ₅ | | 4 | % | | |
| | NiO | | 0,07 | % | | |
| | P ₂ O ₅ | | 0,02 | % | | |
| | SiO ₂ | | 41 | % | | |
| | Ta ₂ O ₃ | | 0,4 | % | | |
| | TiO ₂ | | 5 | % | | |
| | V ₂ O ₅ | | 5,5 | % | | |