

### **Glass, SUS, Disc 40 mm Ø x 5 mm**

Art. ID	XRF-BR-ME2
Unit	disc
Deliverydetails	No Dangerous Good /not restricted

#### **Description**

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Ag <sub>2</sub> O		0,026	%		
	Al <sub>2</sub> O <sub>3</sub>		10	%		
	CaO		20	%		
	CdO		0,028	%		
	CoO		0,031	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,036 (Cr <sub>2</sub> O <sub>5</sub> )	%		
	CuO		0,031	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,036	%		
	MgO	[1309-48-4]	15	%		
	MnO <sub>2</sub>		0,04	%		
	MoO <sub>3</sub>		0,037	%		
	Na <sub>2</sub> O		0,033	%		
	P <sub>2</sub> O <sub>5</sub>		2	%		
	PbO		0,026	%		
	SiO <sub>2</sub>		52,53	%		
	SrO		0,03	%		
	TiO <sub>2</sub>		0,041	%		
	V <sub>2</sub> O <sub>5</sub>		0,044	%		
	ZnO		0,031	%		