

**Glass, SUS, Disc 40 mm Ø x 5 mm**

|                 |                                   |
|-----------------|-----------------------------------|
| Art. ID         | XRF-BR-TAB5                       |
| Unit            | disc                              |
| Deliverydetails | No Dangerous Good /not restricted |

**Description**

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 3                   | %    |        |        |
|                  | B <sub>2</sub> O <sub>3</sub>  |             | 15                  | %    |        |        |
|                  | BaO                            |             | 2                   | %    |        |        |
|                  | MgO                            | [1309-48-4] | 28                  | %    |        |        |
|                  | Na <sub>2</sub> O              |             | 10                  | %    |        |        |
|                  | PbO                            |             | 3                   | %    |        |        |
|                  | Sb <sub>2</sub> O <sub>3</sub> |             | 0,6                 | %    |        |        |
|                  | SiO <sub>2</sub>               |             | 38,4                | %    |        |        |