

Iron Ore Sinter Powder

Art. ID BS-104A
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		1,04	%		
	Carbon (C)	[7440-44-0]	0,22	%		
	CaO		10,5	%		
	Iron (Fe)	[7439-89-6]	54,8 (tot)	%		
	K ₂ O		0,14	%		
	MgO	[1309-48-4]	1,24	%		
	MnO		1,06	%		
	Na ₂ O		0,022	%		
	P ₂ O ₅		0,101	%		
	Sulfur (S)	[7704-34-9]	0,015	%		
	SiO ₂		7,97	%		
	TiO ₂		0,094	%		