

## **Iron Ore Sinter Powder**

Art. ID                      BS-104A  
Unit                         100 g (powder)  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		1,04	%		
	Carbon (C)	[7440-44-0]	0,22	%		
	CaO		10,5	%		
	Iron (Fe)	[7439-89-6]	54,8 (tot)	%		
	K <sub>2</sub> O		0,14	%		
	MgO	[1309-48-4]	1,24	%		
	MnO		1,06	%		
	Na <sub>2</sub> O		0,022	%		
	P <sub>2</sub> O <sub>5</sub>		0,101	%		
	Sulfur (S)	[7704-34-9]	0,015	%		
	SiO <sub>2</sub>		7,97	%		
	TiO <sub>2</sub>		0,094	%		