

**Bauxite, CRM, Available Alumina: 59.3%, Reactive Silica: 0.52%, Powder**

Art. ID                    CETEM-BXGO-1  
Unit                        120 g (powder)  
Deliverydetails        No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		60,7	%		
	Organic C		~0,12	%		
	CaO		~0,02	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,01	%		
	CuO		~0,0002	%		
	Fe <sub>2</sub> O <sub>3</sub>		4,6	%		
	Ga <sub>2</sub> O <sub>3</sub>		~0,006	%		
	K <sub>2</sub> O		~0,004	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO <sub>2</sub>		0,005	%		
	Na <sub>2</sub> O		~0,006	%		
	P <sub>2</sub> O <sub>5</sub>		0,042	%		
	SO <sub>3</sub>		~0,22	%		
	SiO <sub>2</sub>		0,63	%		
	TiO <sub>2</sub>		0,46	%		
	V <sub>2</sub> O <sub>5</sub>		0,017	%		
	ZnO		~0,002	%		
	ZrO <sub>2</sub>		~0,003	%		