

Bauxite, CRM, Available Alumina: 59.3%, Reactive Silica: 0.52%, Powder

Art. ID CETEM-BXGO-1
Unit 120 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		60,7	%		
	Organic C		~0,12	%		
	CaO		~0,02	%		
	Cr ₂ O ₃		0,01	%		
	CuO		~0,0002	%		
	Fe ₂ O ₃		4,6	%		
	Ga ₂ O ₃		~0,006	%		
	K ₂ O		~0,004	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO ₂		0,005	%		
	Na ₂ O		~0,006	%		
	P ₂ O ₅		0,042	%		
	SO ₃		~0,22	%		
	SiO ₂		0,63	%		
	TiO ₂		0,46	%		
	V ₂ O ₅		0,017	%		
	ZnO		~0,002	%		
	ZrO ₂		~0,003	%		