

Bauxite, CRM, Available Alumina: 45.5%, Reactive Silica: 1.88%, Powder

Art. ID CETEM-BXMG-2
Unit 135 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		50,4	%		
	Organic C		~0,1	%		
	CaO		~0,01	%		
	Cr ₂ O ₃		0,028	%		
	CuO		~0,004	%		
	Fe ₂ O ₃		13,7	%		
	Ga ₂ O ₃		~0,008	%		
	K ₂ O		0,013	%		
	MgO	[1309-48-4]	~0,04	%		
	MnO ₂		0,016	%		
	Na ₂ O		~0,01	%		
	P ₂ O ₅		0,209	%		
	SO ₃		~0,15	%		
	SiO ₂		6,36	%		
	TiO ₂		1,64	%		
	V ₂ O ₅		0,035	%		
	ZnO		~0,004	%		
	ZrO ₂		0,042	%		