

Bauxite, CRM, Available Alumina: 33.2%, Reactive Silica: 0.75%, Powder

Art. ID CETEM-BXMG-3
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		37,9	%		
	Organic C		~0,39	%		
	CaO		~0,02	%		
	Cr ₂ O ₃		0,029	%		
	CuO		~0,003	%		
	Fe ₂ O ₃		35,3	%		
	Ga ₂ O ₃		~0,01	%		
	K ₂ O		0,021	%		
	MgO	[1309-48-4]	~0,04	%		
	MnO ₂		0,102	%		
	Na ₂ O		~0,02	%		
	P ₂ O ₅		0,184	%		
	SO ₃		~0,13	%		
	SiO ₂		2,29	%		
	TiO ₂		2,01	%		
	V ₂ O ₅		0,051	%		
	ZnO		~0,005	%		
	ZrO ₂		0,05	%		