

**Bauxite, CRM, Available Alumina: 33.2%, Reactive Silica: 0.75%, Powder**

Art. ID                    CETEM-BXMG-3  
Unit                        100 g (powder)  
Deliverydetails        No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		37,9	%		
	Organic C		~0,39	%		
	CaO		~0,02	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,029	%		
	CuO		~0,003	%		
	Fe <sub>2</sub> O <sub>3</sub>		35,3	%		
	Ga <sub>2</sub> O <sub>3</sub>		~0,01	%		
	K <sub>2</sub> O		0,021	%		
	MgO	[1309-48-4]	~0,04	%		
	MnO <sub>2</sub>		0,102	%		
	Na <sub>2</sub> O		~0,02	%		
	P <sub>2</sub> O <sub>5</sub>		0,184	%		
	SO <sub>3</sub>		~0,13	%		
	SiO <sub>2</sub>		2,29	%		
	TiO <sub>2</sub>		2,01	%		
	V <sub>2</sub> O <sub>5</sub>		0,051	%		
	ZnO		~0,005	%		
	ZrO <sub>2</sub>		0,05	%		