

Bauxite, CRM, Available Alumina: 40.7%, Reactive Silica: 5.9%, Powder

Art. ID CETEM-BXMG-4
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		50,4	%		
	Organic C		~0,27	%		
	CaO		~0,03	%		
	Cr ₂ O ₃		~0,002	%		
	CuO		~0,0008	%		
	Fe ₂ O ₃		9,9	%		
	Ga ₂ O ₃		~0,011	%		
	K ₂ O		0,77	%		
	MgO	[1309-48-4]	~0,04	%		
	MnO ₂		0,34	%		
	Na ₂ O		~0,04	%		
	P ₂ O ₅		0,144	%		
	SO ₃		~0,06	%		
	SiO ₂		9,5	%		
	TiO ₂		1,78	%		
	V ₂ O ₅		0,035	%		
	ZnO		0,014	%		
	ZrO ₂		0,24	%		