

Bauxite, CRM, Available Alumina: 39.7%, Reactive Silica: 7.8%, Powder

Art. ID CETEM-BXMG-5
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		50,5	%		
	Organic C		~0,5	%		
	CaO		~0,02	%		
	Cr ₂ O ₃		~0,004	%		
	CuO		~0,0008	%		
	Fe ₂ O ₃		9,2	%		
	Ga ₂ O ₃		~0,011	%		
	K ₂ O		0,54	%		
	MgO	[1309-48-4]	~0,04	%		
	MnO ₂		0,34	%		
	Na ₂ O		~0,03	%		
	P ₂ O ₅		0,111	%		
	SO ₃		~0,05	%		
	SiO ₂		10,7	%		
	TiO ₂		1,28	%		
	V ₂ O ₅		0,03	%		
	ZnO		0,012	%		
	ZrO ₂		0,25	%		