

**Bauxite, CRM, Available Alumina: 49.0%, Reactive Silica: 3.8%, Powder**

Art. ID                    CETEM-BXPA-1  
Unit                      140 g (powder)  
Deliverydetails        No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		27,5	%		
	Al <sub>2</sub> O <sub>3</sub>		52,8	%		
	Fe <sub>2</sub> O <sub>3</sub>		12,8	%		
	MnO		~0,0017	%		
	P <sub>2</sub> O <sub>5</sub>		~0,018	%		
	SiO <sub>2</sub>		~4,93	%		
	TiO <sub>2</sub>		1,42	%		
	V <sub>2</sub> O <sub>5</sub>		0,058	%		
	ZnO		0,004	%		
	ZrO <sub>2</sub>		~0,066	%		