

Bauxite, CRM, Available Alumina: 49.0%, Reactive Silica: 3.8%, Powder

Art. ID CETEM-BXPA-1
Unit 140 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		27,5	%		
	Al ₂ O ₃		52,8	%		
	Fe ₂ O ₃		12,8	%		
	MnO		~0,0017	%		
	P ₂ O ₅		~0,018	%		
	SiO ₂		~4,93	%		
	TiO ₂		1,42	%		
	V ₂ O ₅		0,058	%		
	ZnO		0,004	%		
	ZrO ₂		~0,066	%		