

**Bauxite, CRM, Available Alumina: 50.6%, Reactive Silica: 4.2%, Powder**

Art. ID                    CETEM-BXPA-2  
Unit                        100 g (powder)  
Deliverydetails        No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		55,4	%		
	Organic C		~0,05	%		
	CaO		~0,01	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,013	%		
	CuO		~0,0006	%		
	Fe <sub>2</sub> O <sub>3</sub>		9,2	%		
	Ga <sub>2</sub> O <sub>3</sub>		~0,01	%		
	K <sub>2</sub> O		~0,0000004	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO <sub>2</sub>		~0,0013	%		
	Na <sub>2</sub> O		~0,01	%		
	P <sub>2</sub> O <sub>5</sub>		0,016	%		
	SO <sub>3</sub>		~0,07	%		
	SiO <sub>2</sub>		4,91	%		
	TiO <sub>2</sub>		1,35	%		
	V <sub>2</sub> O <sub>5</sub>		0,035	%		
	ZnO		~0,003	%		
	ZrO <sub>2</sub>		0,073	%		