

Bauxite, CRM, Available Alumina: 50.6%, Reactive Silica: 4.2%, Powder

Art. ID CETEM-BXPA-2
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		55,4	%		
	Organic C		~0,05	%		
	CaO		~0,01	%		
	Cr ₂ O ₃		0,013	%		
	CuO		~0,0006	%		
	Fe ₂ O ₃		9,2	%		
	Ga ₂ O ₃		~0,01	%		
	K ₂ O		~0,0000004	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO ₂		~0,0013	%		
	Na ₂ O		~0,01	%		
	P ₂ O ₅		0,016	%		
	SO ₃		~0,07	%		
	SiO ₂		4,91	%		
	TiO ₂		1,35	%		
	V ₂ O ₅		0,035	%		
	ZnO		~0,003	%		
	ZrO ₂		0,073	%		