

Bauxite, CRM, Available Alumina: 49.8%, Reactive Silica: 3.4%, Powder

Art. ID CETEM-BXPA-3
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		53,7	%		
	Organic C		~0,06	%		
	CaO		~0,01	%		
	Cr ₂ O ₃		0,016	%		
	CuO		~0,001	%		
	Fe ₂ O ₃		11,6	%		
	Ga ₂ O ₃		~0,01	%		
	K ₂ O		~0,011	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO ₂		0,045	%		
	Na ₂ O		~0,02	%		
	P ₂ O ₅		0,042	%		
	SO ₃		~0,09	%		
	SiO ₂		4,19	%		
	TiO ₂		1,92	%		
	V ₂ O ₅		0,029	%		
	ZnO		~0,003	%		
	ZrO ₂		0,21	%		