

Bauxite, CRM, Available Alumina: 52.7%, Reactive Silica: 3.7%, Powder

Art. ID CETEM-BXPA-4
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		57,3	%		
	Organic C		~0,05	%		
	CaO		~0,01	%		
	Cr ₂ O ₃		0,007	%		
	CuO		~0,0008	%		
	Fe ₂ O ₃		6,9	%		
	Ga ₂ O ₃		~0,009	%		
	K ₂ O		~0,009	%		
	MgO	[1309-48-4]	~0,03	%		
	MnO ₂		0,037	%		
	Na ₂ O		~0,02	%		
	P ₂ O ₅		0,027	%		
	SO ₃		~0,05	%		
	SiO ₂		4,65	%		
	TiO ₂		1,31	%		
	V ₂ O ₅		0,018	%		
	ZnO		~0,002	%		
	ZrO ₂		0,16	%		