

Bauxite, CRM, Available Alumina: 40.0%, Reactive Silica: 7.8%, Powder

Art. ID CETEM-BXSP-1
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		50,1	%		
	Organic C		~0,64	%		
	CaO		~0,03	%		
	Cr ₂ O ₃		0,003	%		
	CuO		~0,001	%		
	Fe ₂ O ₃		6,7	%		
	Ga ₂ O ₃		~0,01	%		
	K ₂ O		0,53	%		
	MgO	[1309-48-4]	~0,06	%		
	MnO ₂		0,07	%		
	Na ₂ O		~0,02	%		
	P ₂ O ₅		0,203	%		
	SO ₃		~0,07	%		
	SiO ₂		14,7	%		
	TiO ₂		1,24	%		
	V ₂ O ₅		0,016	%		
	ZnO		0,009	%		
	ZrO ₂		0,15	%		