

Cement, CRM, Powder

Art. ID FLX-CRM103
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~0,59 | % | | |
| | Al ₂ O ₃ | | 7,75 | % | | |
| | CaO | | 54,9 | % | | |
| | Chlorine (Cl) | [7782-50-5] | ~0,04 | % | | |
| | Cr ₂ O ₃ | | 0,007 | % | | |
| | Fe ₂ O ₃ | | 1,78 | % | | |
| | K ₂ O | | 0,77 | % | | |
| | MgO | [1309-48-4] | 4,44 | % | | |
| | Mn ₂ O ₃ | | 0,17 | % | | |
| | Na ₂ O | | 0,33 | % | | |
| | P ₂ O ₅ | | 0,09 | % | | |
| | SO ₃ | | 2,73 | % | | |
| | SiO ₂ | | 26,95 | % | | |
| | SrO | | 0,07 | % | | |
| | TiO ₂ | | 0,372 | % | | |
| | ZnO | | 0,014 | % | | |