

Cement, CRM, Powder

Art. ID FLX-CRM106
Unit 30 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~2,06 | % | | |
| | Al ₂ O ₃ | | 5,7 | % | | |
| | CaO | | 66,05 | % | | |
| | Chlorine (Cl) | [7782-50-5] | 0,055 | % | | |
| | Cr ₂ O ₃ | | 0,008 | % | | |
| | Fe ₂ O ₃ | | 1,98 | % | | |
| | K ₂ O | | 0,86 | % | | |
| | MgO | [1309-48-4] | 0,96 | % | | |
| | Mn ₂ O ₃ | | 0,161 | % | | |
| | Na ₂ O | | 0,12 | % | | |
| | P ₂ O ₅ | | 0,111 | % | | |
| | SO ₃ | | 3,01 | % | | |
| | SiO ₂ | | 20,29 | % | | |
| | SrO | | 0,206 | % | | |
| | TiO ₂ | | 0,271 | % | | |
| | ZnO | | 0,012 | % | | |