

Cement, RM, Powder

Art. ID JCA-RM-612
Unit 30 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~2,52 | % | | |
| | Al ₂ O ₃ | | 5,19 | % | | |
| | CaO | | 62,95 | % | | |
| | Fe ₂ O ₃ | | 2,81 | % | | |
| | K ₂ O | | 0,9 | % | | |
| | MgO | [1309-48-4] | 1,52 | % | | |
| | MnO | | 0,06 | % | | |
| | Na ₂ O | | 0,52 | % | | |
| | P ₂ O ₅ | | 1,02 | % | | |
| | SO ₃ | | 4,51 | % | | |
| | SiO ₂ | | 20,12 | % | | |
| | SrO | | 0,045 | % | | |
| | TiO ₂ | | 0,28 | % | | |