

Bauxite, CRM, Burned Bauxite, Powder

Art. ID JCRM-R301
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|-------------------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | 0,35 | % | | |
| | Al ₂ O ₃ | | 87,5 | % | | |
| | CaO | | 0,03 | % | | |
| | Fe ₂ O ₃ | | 1,4 | % | | |
| | K ₂ O | | 0,04 | % | | |
| | MgO | [1309-48-4] | 0,02 | % | | |
| | Na ₂ O | | 0,03 | % | | |
| | P ₂ O ₅ | | 0,07 | % | | |
| | SiO ₂ | | 7,24 | % | | |
| | TiO ₂ | | 2,9 | % | | |
| | ZrO ₂ | | 0,13 (incl HfO ₂) | % | | |