

Bauxite, CRM, Burned Bauxite, Powder

Art. ID JCRM-R301
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,35	%		
	Al ₂ O ₃		87,5	%		
	CaO		0,03	%		
	Fe ₂ O ₃		1,4	%		
	K ₂ O		0,04	%		
	MgO	[1309-48-4]	0,02	%		
	Na ₂ O		0,03	%		
	P ₂ O ₅		0,07	%		
	SiO ₂		7,24	%		
	TiO ₂		2,9	%		
	ZrO ₂		0,13 (incl HfO ₂)	%		