

Siliceous Material, CRM, only available as set, please see JCRM-R404-R406, Powder

Art. ID JCRM-R405
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,13	%		
	Al ₂ O ₃		1,07	%		
	CaO		0,029	%		
	Fe ₂ O ₃		0,053	%		
	K ₂ O		0,71	%		
	MgO	[1309-48-4]	0,023	%		
	Na ₂ O		0,06	%		
	SiO ₂		97,78	%		
	TiO ₂		0,022	%		