

Siliceous Material, CRM, only available as set, please see JCRM-R404-R406, Powder

Art. ID JCRM-R406
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,97	%		
	Al ₂ O ₃		1,31	%		
	CaO		0,016	%		
	Fe ₂ O ₃		0,102	%		
	K ₂ O		0,13	%		
	MgO	[1309-48-4]	0,005	%		
	Na ₂ O		0,03	%		
	SiO ₂		96,71	%		
	TiO ₂		0,564	%		