

Siliceous Material, CRM, Gairome Clay, only available as set, please see JCRM-R604-R605-R751, Powder

Art. ID JCRM-R604
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		13,37	%		
	Al ₂ O ₃		35,37	%		
	CaO		0,216	%		
	Fe ₂ O ₃		1,357	%		
	K ₂ O		0,468	%		
	MgO	[1309-48-4]	0,251	%		
	MnO		0,006	%		
	Na ₂ O		0,083	%		
	P ₂ O ₅		0,02	%		
	Sulfur (S)	[7704-34-9]	~0,014	%		
	SiO ₂		47,88	%		
	TiO ₂		0,865	%		