

Siliceous Material, CRM, Kaolin, only available as set, please see JCRM-R604-R605-R751, Powder

Art. ID JCRM-R605
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		13,9	%		
	Al ₂ O ₃		35,64	%		
	CaO		0,004	%		
	Fe ₂ O ₃		0,283	%		
	K ₂ O		~0,008	%		
	MgO	[1309-48-4]	0,004	%		
	Na ₂ O		0,032	%		
	P ₂ O ₅		0,105	%		
	Sulfur (S)	[7704-34-9]	~0,023	%		
	SiO ₂		49,77	%		
	TiO ₂		0,068	%		