

Siliceous Material, CRM, Albite, only available as set, please see JCRM-R702-R703-R803, Powder

Art. ID JCRM-R702
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,23	%		
	Al ₂ O ₃		19,64	%		
	CaO		0,546	%		
	Fe ₂ O ₃		0,058	%		
	K ₂ O		0,137	%		
	MgO	[1309-48-4]	0,103	%		
	MnO		0,004	%		
	Na ₂ O		11,31	%		
	P ₂ O ₅		0,139	%		
	SiO ₂		67,69	%		
	TiO ₂		0,03	%		