

Siliceous Material, CRM, Potassium Feldspar, only available as set, please see JCRM-R702-R703-R803, Powder

Art. ID JCRM-R703
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,36	%		
	Al ₂ O ₃		17,93	%		
	CaO		0,095	%		
	Fe ₂ O ₃		0,082	%		
	K ₂ O		11,02	%		
	MgO	[1309-48-4]	0,04	%		
	MnO		0,003	%		
	Na ₂ O		3,32	%		
	P ₂ O ₅		0,008	%		
	SiO ₂		66,99	%		
	TiO ₂		0,005	%		